

# Synolite™ 5410-P-2

## Multi-purpose Hand lay-up resin with Low Styrene Emission capability

Synolite™ 5410-P-2 is a versatile Ortho resin for Hand lay-up and Spray-up processes with Low Styrene Emission (LSE) system and fast gel time.

The resin is particularly suited for Marine applications and is Lloyd's Register approved.

### Benefits

- Easy and robust processing
- Can be used both for making thick and thin laminates
- Enhanced secondary bonding capability
- Reduced Styrene emissions compared to equivalent competitive Ortho resins

## Major Applications

Synolite™ 5410-P-2 resin has been specially developed for Hand lay-up and Spray-up applications to produce a variety of structural laminates.

Synolite™ 5410-P-2 resin combines short gel time and gradual Cure for optimal process-ability. This resin shows good fiber wetting and impregnation properties and can be used with a broad range of glass mats.

Thick laminates can be made in one go due to low exothermic heat development combined with good through cure, even in thin laminates.

An LSE system is incorporated in the resins for obtaining excellent low styrene emissions.

## Product Specifications

Property	Value	Unit	TM
Appearance	Hazy		TM 2265
Solids content	53 - 57	%	TM 2033
Viscosity 23 °C, 2 s <sup>-1</sup>	950 - 1200	mPa.s	TM 2313
Viscosity 23 °C, 20 s <sup>-1</sup>	330 - 450	mPa.s	TM 2313
Viscosity 23 °C, 250 s <sup>-1</sup>	190 - 220	mPa.s	TM 2313
Gel time 25 until 35 °C	10 - 14	min	TM 2625
Peak time	22 - 32	min	TM 2625
Peak temperature	65 - 105	°C	TM 2625

Viscosity measurement: TM 2313: spindle Z2, 23°C. Curing conditions at 25°C, TM 2625: 2.0 g Medium reactive Methyl Ethyl Ketone peroxide (MEKP) in 100 g resin.

## Liquid

Property	Value	Unit	TM
Density 23 °C	1100	kg/m <sup>3</sup>	TM 2160
Flash point	33	°C	TM 2800
Stability (no initiator, dark, 25°C)	6	month	
Color	Blue	-	

## Solid Unfilled

Property	Value	Unit	TM
Density 23 °C	1150	kg/m <sup>3</sup>	DIN 53479
Tensile strength	70	MPa	ISO 527-2
Tensile modulus	4	GPa	ISO 527-2
Elongation at break	2.1	%	ISO 527-2
Flexural strength	115	MPa	ISO 178
Flexural E-Modulus	4	GPa	ISO 178
HDT	63	°C	ASTM D648
Impact strength	12	kJ/m <sup>2</sup>	ISO 179

Cured with 1% Medium reactive Methyl Ethyl Ketone Peroxide (MEKP) peroxide. Post cured 24 h at RT followed by 24 h at 70°C.

## Application Guidelines

Synolite™ 5410-P-2 resin contains barrier forming agents to reduce emission of styrene. These agents may reduce the bonding strength of over-laminating. Good strength can be obtained with over-laminating of the base laminate after delayed lay-up if the surface is not too resin rich. In other cases the surface may require sanding.

The resin should be conditioned at 15°C minimum before use to obtain a sufficient cure when MEKP is used as a curing system. Stir the resin mechanically before use. Do not use air bubbles to stir the resin.

## Storage Guidelines

The resin should be stored indoors in a dry place at temperature tight and undamaged packaging.

The properties of the resin may change slightly during storage.

## Material Safety

A Material Safety Data Sheet of this product is available on request.

## Test Methods

Test methods (TM) referred to in the table(s) are available on request.

## ISO 9001:2015 Certified

The Quality Management Systems at every AOC manufacturing facility have been certified as meeting ISO 9001:2015 standards. This certification recognizes that each AOC facility has an internationally accepted model in place for managing and assuring quality. We follow the practices set forth in this model to add value to the resins we make for our customers.

## AOC. Trusted Solutions

AOC is the leading global supplier of resins and specialty materials which enable customers to create robust, durable and versatile products and components. With strong capabilities around the world in manufacturing and science, the company works closely with customers to deliver unrivaled quality, service and reliability for today, and create innovative solutions for tomorrow. Partner with AOC and we will work together to find the right solutions for your business.

### Contact us for more information

We will help you to choose the right resin solution.

[emea@aocresins.com](mailto:emea@aocresins.com)

Europe, Middle East & Africa  
+41 52 6441212  
[emea@aocresins.com](mailto:emea@aocresins.com)

**AOC**  
**Trusted Solutions**

AOC is a registered trademark of the AOC group of companies.

The user is held responsible for checking the quality, safety and all other properties of our products prior to use. The information and recommendations contained herein are to the best of our knowledge accurate and reliable, but no rights whatsoever may be derived by any party other than those expressly agreed to with a selling entity of the AOC group of companies in a legally binding agreement. AOC hereby makes no warranty of any kind, express or implied, including those of merchantability and fitness for purpose. Unless explicitly agreed to in writing by AOC otherwise, all offers, quotations, sales and deliveries of AOC products are subject to the general conditions of sale of AOC. Atlac®, Beyone®, Daron®, NeoMould®, Neoxil®, Palatal®, Palapreg®, Synolite™, the AOC™ name, the AOC™ logo and the Trusted Solutions™ logo are the registered trademarks of the AOC group of companies

For more information: [aocresins.com](http://aocresins.com)